

RonaScreed 4 Day Overlay Quick Drying Screed

Pre-packed quick drying screed



FEATURES

- rapid hardening—light foot traffic in 24 hours
- rapid drying—can receive floor coverings such as vinyl, tiles and carpet after 4 days @ 50mm thick
- rapid early strength development
- pre-packed formulation offers assurance of consistent high performance
- apply as a bonded screed from 35mm, unbonded from 50mm and floating from 65mm minimum thickness
- compressive strength >40N/mm² after 28 days
- suitable for screed pumps—consult technical department
- compatible with underfloor heating systems

Description

RonaScreed 4 Day Overlay Quick Drying Screed additive for site batched screeds is used to quickly reduce the level of retained moisture within the screed allowing floor coverings to be laid over the screed much sooner than with conventional screeds. Rapid strength gain permits early access by following trades.

RonaScreed 4 Day Overlay Quick Drying Screed is supplied in powder form. Each 3kg sachet is sufficient for a 25kg bag of cement. It promotes rapid drying and early laying of floor coverings such as sheet vinyl, tiles and other materials including the range of RonaFloor Epoxy and Polyurethane coatings (refer to Ronacrete Technical Department).

RonaScreed 4 Day Overlay Quick Drying Screed additive is typically incorporated within 35mm to 75mm thick floor screeds and applied by competent screeding and floor laying contractors. RonaScreed 4 Day Overlay Quick Drying Screed can be purchased and laid by non-licensed screeding contractors.

Drying Time of 50mm screed

1 day	84%
2 days	80%
3 days	76%
4 days	74%

The accepted figure for the laying of vinyl floor coverings, tiles etc is 75%. Also refer to “Drying”

The data is based on drying @ 20°C in good drying conditions. Low temperature, high humidity, slow air movement and other poor drying conditions will delay the drying times. If the screed is covered with a curing membrane such as polythene, then the drying time starts when the membrane is removed. The relative humidity

RonaScreed 4 Day Overlay Quick Drying Screed

Pre-packed quick drying screed

Drying Time of 50mm Screed (continued) (RH) at the surface of the screed should be measured with a hygrometer before proceeding to lay floor coverings. Standard practices should be followed.

Physical Properties	Compressive Strength	
	1 day	30N/mm ²
	28 days	68N/mm ²

The above are typical laboratory results @ 20°C. Site strengths will be lower.

Yield and Coverage	Required per m² @ 50mm	3kg
	Required per m² @ 75mm	4.5kg
	Required per m³	60kg

Mix Design	Portland cement	50kg (1)
	Medium grade sharp sand	150kg (2.5)
	RonaScreed 4 Day Overlay Quick Drying Screed	6kg
	Water	18 litres approx
	Yield per mix	0.1m³

Measuring Surface Drying Drying concrete must be separated from the screed by polythene or RonaScreed DPM surface damp proof membrane. Screeds thicker than those referred to will take longer to dry out. Screeds which are wetted during their application or curing will take longer to dry out.

Note that RonaScreed screeds are designed to be covered with carpet, vinyl, tiles or other coverings and are not designed as wearing screeds or toppings. For wearing screeds Ronafix or RonaScreed Self Smoothing Topping should be used.

Areas of Use RonaScreed 4 Day Overlay Quick Drying Screed screeds can be laid in the following situations:

- over concrete slabs
- over existing screeds
- on to damp proof membranes (minimum thickness 35mm on to RonaScreed DPM)
- on insulating board (minimum thickness 65mm)
- unbonded on precast concrete, slabs/planks
- unbonded on lightweight screeds

RonaScreed 4 Day Overlay Quick Drying Screed

Pre-packed quick drying screed

Areas of Use (continued)

All RonaScreed 4 Day Overlay Quick Drying Screed mix designs meet the requirements of Category A, BS8204 Part 1 and are therefore suitable for use in the following areas:

Category A - Very Heavy Traffic

e.g. hospital corridors, operating theatres, x-ray rooms, laboratories

Category B - Heavy Traffic

e.g. canteens, restaurants, hospital wards, main corridors

Category C - Light Traffic

e.g. foot traffic, light trolleys, offices, domestic housing

Drying and Hardening

Floor screeds incorporating RonaScreed 4 Day Overlay Quick Drying Screed dry more quickly than traditional screeds and will generally accept foot traffic after 24 hours only. Vinyl floor coverings and tiles can be laid over a RonaScreed 4 Day Overlay Quick Drying Screed surface as soon as 4 days after laying (for a 50mm screed).

Bonded, Unbonded and Floating Screeds

RonaScreed 4 Day Overlay Quick Drying Screed screeds can be laid either bonded, unbonded or floating. Bonded screeds must be laid on to a suitably prepared substrate (see Surface Preparation). Unbonded screeds are those laid on a separating layer or preformed damp proof membrane. Floating screeds are those laid on to an insulation board or resilient layer.

Bonded Screed (from 35mm)

- suitable substrate, mechanically prepared (and optionally covered with RonaScreed DPM)
- prime with Ronacrete Standard Primer

Bonded Screed (from 50mm)

- suitable substrate, mechanically prepared
- primer with cement : water (2:1)

Unbonded Screed (from 50mm)

- solid substrate with polythene or other suitable membrane

Floating Screed (65mm)

- light use
- insulation board

Floating Screed (75mm)

- heavy use
- insulation board

RonaScreed 4 Day Overlay Quick Drying Screed

Pre-packed quick drying screed

Damp Proof Membrane

A damp proof membrane should be present under the concrete slab to prevent moisture penetration from below. If no membrane is present or if the concrete is drying, apply two coats of RonaScreed DPM or install a sheet or similar membrane. If RonaScreed DPM is laid on to a clean, sound substrate as specified in the RonaScreed DPM data sheet it is possible to lay RonaScreed 4 Day Overlay Quick Drying Screed at a minimum thickness of 35mm, bonded to the RonaScreed DPM with a primer of Ronafix and cement

Mix Components and Design

The basic components of a RonaScreed 4 Day Overlay Quick Drying Screed screed are cement CEM1 52.5R for strength and Drying time as shown in the data sheet, and sand from grades 0/2 or 0/4 to BS EN 126208, RonaScreed 4 Day Overlay Quick Drying Screed and clean water. The water content shown in mix designs must be adhered to, dry mixes will fail to fully hydrate the cement. Larger sized aggregates are used for concrete or granolithic finishes.

RonaScreed 4 Day Overlay Quick Drying Screed mix 1 gives a water/cement ratio of 0.36 and yields approximately 0.1m³. The density of the cured screed is approximately 2300kg/m³. This mix design can be altered to 1:4 (cement : sand) by weight if preferred, but strength will be reduced.

Aggregate Water Content

If damp sand is used the amount of water should be adjusted accordingly.

Instructions for Use

Surface Preparation for bonded screeds

The surface on to which a RonaScreed 4 Day Overlay Quick Drying Screed screeds is to be bonded must be clean, structurally sound and stable. All grease, oil, laitance and loose material must be removed. The surface must be keyed to expose the aggregate and to provide good adhesion. This is best achieved by scabbling, planing or blasting. The prepared surface must be cleaned (ideally by vacuum), damped with clean water and excess water removed.

Mixing

RonaScreed 4 Day Overlay Quick Drying Screed must be mixed using a forced action mixer to provide maximum workability and compaction with the minimum amount of liquid required to fully hydrate the cement. Dry mix the cement and sand then add the RonaScreed 4 Day Overlay Quick Drying Screed powder followed by sufficient clean water to provide the desired level of workability. The screeder should be able to make a ball of the mixed mortar and pull it apart without crumbling of the mortar.

Priming

Where thickness dictates the use of a bonding coat, the prepared surface must be well damped with clean water and the water allowed to soak in.

Excess water must be removed and the appropriate bond coat applied. For bonded screeds this is a mix of 1:1 Ronafix:cement brushed in to the surface

RonaScreed 4 Day Overlay Quick Drying Screed

Pre-packed quick drying screed

Instructions for Use (continued)

or, depending on thickness, a 2:1 cement/water slurry. Before this dries the screed must be laid. If the bonding coat dries it must be vigorously scratched and reapplied.

Laying

Standard screeding practices should be followed. The mortar must be placed as soon as possible after mixing and well consolidated. Conventional tools such as float and trowel are used to obtain the desired surface finish.

Embedded Conduits and Pipes

When laying conduits or pipes within RonaScreed 4 Day Overlay Quick Drying Screed screeds the conduit or pipe should be a minimum of 25mm beneath the top surface. It is advisable to incorporate reinforcing mesh centrally within the depth of the screed over the conduit or pipe, extending for not less than 150mm each side to minimise the risk of cracking.

Bay Sizes

RonaScreed 4 Day Overlay Quick Drying Screed should be laid as one continuous area, taking care to observe the following:

- construction joints in the substrate must be expressed through into the screed
- expansion joints in the substrate must be expressed through into the screed
- when laying on suspended floors movement joints should be installed in the screed over support positions to accommodate movement
- isolation joints should be installed around the perimeter of the floor and around columns, manholes and fixed spaces to accommodate movement

Curing

Curing must commence as soon as possible after finishing the screed. Cure the screed with tight fitting polythene, placed on to the screed as early as possible without damaging the surface. Cover for 24 hours then remove and air cure.

Laying on to Precast Planks

When laying RonaScreed 4 Day Overlay Quick Drying Screed on to precast planks the screed should ideally be laid unbonded with a separating membrane. If the screed can not be laid thick enough to be unbonded the planks should either be provided with an acceptable rough clean laitance free finish or be lightly shot blasted and vacuum cleaned. The screed should be bonded using a primer of 1:1 Ronafix :cement. Hairline cracks forming in line with the joints between the units will not be detrimental to the screed provided the screed is well bonded but cracking must be expected.

Reinforcing the screed with a suitable mesh (e.g. D49 mesh placed in the middle third of the screed) may be appropriate for particular types of suspended floor design.

Pumping

RonaScreed 4 Day Overlay Quick Drying Screed modified screeds can be pumped to the point of laying. Tests have been conducted using Putzmeister equipment and specific guidance should be sought from Ronacrete Ltd.

RonaScreed 4 Day Overlay Quick Drying Screed

Pre-packed quick drying screed

Testing	As sections of screed are completed the strength of the screed can be measured using a BRE Screedtester.
Contractors	<p>Ronacrete Ltd maintains a list of national and local contractors who are familiar with this type of flooring system and their application procedure but unlike other screeds of a similar nature RonaScreed 4 Day Overlay Pre-packed Quick Drying Screed can be purchased and applied by competent screeding contractors throughout the country.</p> <p>There are obvious advantages in selecting a contractor who has previous experience of the material but if requested the Ronacrete Technical Department will provide guidance and assistance to other contractors.</p>
Other Flooring Materials	<p>Depending on the specific requirements of the floor system being laid Ronacrete may recommend an alternative product and specification which may be more suited to the application.</p> <p>To discuss the use of Ronacrete materials for any application please contact the Ronacrete Technical Department for full technical and practical guidance at design and specification stage together with site assistance and practical backup.</p> <p>Instruction and tuition can also be given to those contractors and specifiers not familiar with Ronacrete products and techniques.</p>
Packaging	RonaScreed 4 Day Overlay Quick Drying Screed is supplied in 18kg packs.
Shelf Life and Storage	RonaScreed 4 Day Overlay Quick Drying Screed should be stored unopened between 5°C and 25°C in dry warehouse conditions and out of direct sunlight. In these conditions shelf life is approximately 9 months.
Health and Safety	RonaScreed 4 Day Overlay Quick Drying Screed is non-flammable and harmful by ingestion. Prolonged contact with skin should be avoided. Any splashes should be washed well with water. If contact with eyes occurs was thoroughly with water and seek medical advice.




RonaScreed 4 Day Overlay Quick Drying Screed

Pre-packed quick drying screed

Site Attendance

When on site Ronacrete representatives are able, if asked, to give a general indication of the correct method of installing a Ronacrete product. It is important to bear in mind that Ronacrete Ltd is a manufacturer and not an application contractor and it is therefore the responsibility of the contractor and his employer to ensure he is aware of and implements the correct practices and procedures to ensure the correct installation of the product and that liability for its correct installation lies with the contractor and not with Ronacrete Ltd.


Ronacrete Ltd, Flex Meadow, Harlow Essex, CM19 5TD, UK
13
BS EN 13813 Floor Screed
Product: RonaScreed 4 Day Overlay Quick Drying Screed Reaction to Fire: A2-s1,d0 Release of Corrosive Substances: None Capillary Water Absorption: < 0.40kg / m² . min0.5 Compressive Strength: > C40 Flexural Strength: > F4 Wear Resistance BCA Method: AR3 Dampness Test (headspace):75% RH at 20C at 4 days Release of Dangerous Substances: Refer to Safety Data Sheet

The information detailed in this leaflet is liable to modification from time to time in the light of experience and of normal product application, and before using, customers are advised to check with Ronacrete Ltd, quoting the reference number, that they possess the latest issue. Any person or company using the product without first making further enquiries as to the suitability of the product for the intended use does so at his own risk, and Ronacrete Ltd can accept no responsibility for the performance of the product, or for any loss or damage arising out of such use.